

SCS225 with Pod Vent

Maroon (case/cover)

Polypropylene

Flooded/wet lead-acid battery

inches (mm)

MODEL:

BATTERY:

MATERIAL:

COLOR:

DIMENSIONS:

SCS225 DATA SHEET





PRODUCT SPECIFICATION

BCI GROUP	ТҮРЕ	CAPACITY ^A Minutes		CRANKING Performance		CAPACITY ^B Amp-Hours (AH)		TERMINAL Type	DIMENSIONS ^c Inches (mm)			WEIGHT lbs. (kg)
SIZE		@25 Amps	@75 Amps	C.C.A. ^D @0°F	C.A. ^E @32°F	5-Hr Rate	20-Hr Rate		Length	Width	Height ^F	
12 VOLT DUAL PURPOSE AGM BATTERY												
30H	SCS225	225	57	665	820	105	130	10	13-15/16 (355)	6-3/4 (171)	9-7/8 (251)	66 (30)

A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are based on nominal performance.
B. The amount of amp-hours (AH) a battery can deliver when discharged at a constant rate at 80°F (27°C) for the 20-Hour and 100-Hour rates and 86°F (30°C) for the 5-Hour rate and maintain a voltage above 1.75 V/cell. Capacities are based on nominal performance.

C. Dimensions are based on nominal size. Dimensions may vary depending on type of handle or terminal.

. C.C.A. (Cold Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F at a voltage above 1.2 V/cell.

E. C.A. (Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F at a voltage above 1.2 V/cell. This is sometimes referred to as marine cranking amps @ 32°F or M. C. A. @ 32°F.

F. Dimensions taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal.

Trojan's battery testing procedures adhere to both BCI and IEC test standards.

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)							
System Voltage	12V	24V	36V	48V			
Daily Charge	14.8	29.6	44.4	59.2			
Float	13.2	26.4	39.6	52.8			
Equalize	15.5	31.0	46.5	62.0			

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

.028 VPC for every 10°F (5.55°C) above or below 77°F (25°C) (add .028 VPC for every 10°F (5.55°C) below 77°F and subtract .028 VPC for every 10°C above 77°F).

OPERATIONAL DATA

Operating Temperature	Self Discharge		
-4°F to 113°F (-20°C to +45°C). At temperatures below 32 °F (0°C) maintain a state of charge greater than 60%.	5 – 15% per month depending on storage temperature conditions.		

TERMINAL CONFIGURATIONS



BATTERY DIMENSIONS (shown with DWNT)







TROJAN SCS225 PERFORMANCE



PERCENT CAPACITY VS. TEMPERATURE





Trojan batteries are available worldwide through Trojan's Master Distributor Network. We offer outstanding technical support, provided by full-time application engineers.

For a Trojan Master Distributor near you, call 800.423.6569 or + 1.562.236.3000 or visit www.trojanbattery.com 12380 Clark Street, Santa Fe Springs, CA 90670 • USA

TRJN_SCS225 • DS0111

© 2010 Trojan Battery Company. All rights reserved. Trojan Battery Company is not liable for damages that may result from any information provided in or omitted from this publication, under any circumstances. Trojan Battery Company reserves the right to make adjustments to this publication at any time, without notices or obligation.